

The original recycled rubber impact sound insulation.
Since 2000.

A flat, resilient, recycled rubber underlayment to be used directly under most floor finishes, yielding exceptional results even under hard surface flooring, over concrete and wood joist construction



PERFORMANCE ATTRIBUTES

- Can thin-set tile and stone directly to the product per ASTM C627
- Compatible with most floor finishes
- Fast installation
- Available in 48" wide rolls and a variety of thicknesses
- Vapor barrier option available

- Crack isolation membrane protects ceramic tile, porcelain and stone tile from substrate cracks
- Rated residential by the Tile Council of North America
- Passes VOC Washington State IAQ Test (ASTM D5116)
- Can contribute toward earning up to 9 LEED

DIMENSIONS

- 12mm in 4' by 15' (1.2m by 4.6m) roll size
- Sheet weight: 1.8lb/ft²
- Standard Tolerances: Width: +3/4" - 0"; Length: +1% - 0"; Thickness: ±0.3mm

ACOUSTICS

Backed by over 400 independent lab and field tests, QTscu 4012 has been proven to provide the highest levels of IIC sound isolation in the industry. Contact us to access the test reports that meet your needs.

SAMPLE RATINGS: IIC 53, STC 57 with porcelain tile, 1 layer QTscu 4012, 8" reinforced concrete slab, no suspended ceiling (ATI D6771 04-113-11-R0)



TECHNICAL DATA

The values shown represent current production based on standard Ecosilencespecs and may vary per thickness. This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

PROPERTY	TEST METHOD	TYPICAL RESULTS
Density	ASTM D297	0.72 g/cm ³ , min.
Thickness	ASTM D3676	12mm (0.472")
Tensile Strength	ASTM D412, Die C	80 psi, min.
Elongation	ASTM D412, Die C	50%, min.
Tear Strength	ASTM D624, Die C	30 ppi, min.
Compression @ 100 psi recovery	ASTM F36	20-30%, 85%, min.
shore A Hardness	ASTM D2240	40
Flexibility	ASTM F147	1 factor, max.
Compression Set B, 25% Deflection, 158°/22 hrs	ASTM D395	40% max.
Coefficient of Friction	ASTM D1894	1.2
Crack Resistance	ANSI 118.12 5.4	High Performance

