



SPEC SHEET

QTSCU 5015

QT Sound Insulation is a high-quality sound control underlayment manufactured in the USA. QT is backed by hundreds of acoustical tests and a team of acoustical engineers to help you provide the right acoustic solution.

PERFORMANCE ATTRIBUTES

- Applicable for a wide range of flooring types (tile, wood, laminate, carpet)
- Vapor barrier option available
- Crack isolation membrane (ANSI A118.12) protects ceramic, porcelain and stone tile from substrate cracks
- Commercially rated by the Tile Council of North America
- Can contribute toward earning up to 9 LEED points
- Supported by over 650 independent lab/field test and a team of acoustical engineers
- Superior long-term acoustical performance-will not degrade over time

DIMENSIONS

- 15mm(.59"); 48" x 15 LF
- Sheet weight: 2.6lb/ft²
- Standard Tolerances: Width: +1/2" - 1/4"; Length: +1% - 0"; Thickness: ±0.4mm

ACOUSTICS

- Tile flooring, QTscu 5015, Hambro D500 composite floor joist system, suspended ceiling –
STC 61 | IIC 58 | HIIC 62 (5005044 and 7005093)
- Engineered wood flooring, QTscu 5015, 3/4" gypsum concrete, TJI joists, RC, 2 layers of gypsum board –
STC 60 | IIC 59 | HIIC 65 (P4252.14)

TECHNICAL DATA

Property	Test Method	Typical Results
Density	ASTM D297	53 lb/ft ³
Thickness	ASTM D3676	15mm (9/16")
Tensile Strength	ASTM D412, Die C	200 psi
Compression @100 psi	ASTM F36	15-25%
Shore A Hardness	ASTM D2240	55



THE ORIGINAL RECYCLED RUBBER IMPACT SOUND INSULATION SINCE 2000.

The values shown represent current production based on standard QTscu specs and may vary per thickness. This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

qtsoundcontrol.com | 866.326.5712

This information reflects most recent test results and is subject to change when necessary.